



ENERGY SAVING SOLUTIONS

AP ArmaFlex[®] AP ArmaFlex[®] FS

Sheet and Roll Insulation

The original fiber-free, flexible elastomeric pipe, valve and duct insulation for reliable protection against condensation, mold and energy loss. AP ArmaFlex FS is PVC free

- // Closed-cell structure provides excellent condensation control
- // Built-in vapor barrier eliminates need for additional vapor retarder
- // 25/50 rated for use in air plenums. Up to:
 - 1" thickness in AP ArmaFlex
 - 1-1/2" and 2" thickness in AP ArmaFlex FS
- // Thickness up to 2" with R-value up to R-8

www.armacell.us



 **armacell**[®]
AP ArmaFlex[®]

TECHNICAL DATA – AP ArmaFlex® and AP ArmaFlex® FS SHEET AND ROLL INSULATION

Description

Black flexible closed-cell elastomeric thermal insulation in sheet and roll form

Specification Compliance

ASTM C 534, Type II — Sheet Grade 1	ASTM G21/C1338	MIL-P-15280J, FORM S ②	UL 181
ASTM C 1534	ASTM G22	MIL-C-3133C (MIL STD 670B)	UL 94 5V-A, V-0, File E55798
ASTM D 1056, 2C1	CAN/ULC S102 ①	Grade SBE 3 ②	City of LA – RR 7642
ASTM E 84, NFPA 255, UL723	MEA 107-89M	NFPA 90A, 90B	

Approvals, Certifications, Compliances

- 3rd party certified by FM Approvals through 1" thickness.
- GREENGUARD Gold Certified.
- Manufactured without CFCs, HFCs, HCFCs, PBDEs, or Formaldehyde.
- Made with EPA registered Microban® antimicrobial product protection.
- All Armacell facilities in North America are ISO 9001:2008 certified.

Typical Properties

Specifications	Values			Test Method
	AP ArmaFlex Through 1"	AP ArmaFlex FS 1-1/2" and 2"	AP ArmaFlex 1-1/2" and 2"	
Thermal Conductivity: Btu • in/h • ft ² • °F (W/mK)				
75°F Mean Temperature [24°C]	0.245 [0.0353]	0.28 [0.040]	0.25 [0.036]	ASTM C 177 or C 518
90°F Mean Temperature [32°C]	0.254 [0.0366]	0.286 [0.041]	0.256 [0.037]	
Water Vapor Permeability: Perm-in. [Kg/[s • m • Pa]]	0.05 [0.725 x 10 ⁻¹³]	0.08 [1.16 x 10 ⁻¹³]	0.05 [0.725 x 10 ⁻¹³]	ASTM E 96, Procedure A
Flame Spread and Smoke Developed Index:	25/50 rated	25/50 rated	Not rated	ASTM E 84 CAN/ULC S102 ①
Water Absorption, % by Volume:	0.2 %	0.2 %	0.2 %	ASTM C 209 or ASTM C1763
Mold Growth:	Passed	Passed	Passed	UL181
Fungi Resistance:				ASTM G21/C1338
Bacterial Resistance:				ASTM G22
Upper Use Limit:	220°F [105°C] ③	300°F [149°C] ④	220°F [105°C] ③	ASTM C534
Lower Use Limit: ⑤	-297°F [-183°C] ⑥	-297°F [-183°C] ⑥	-297°F [-183°C] ⑥	ASTM C534

① AP ArmaFlex meets CAN/ULC S102 through 1" thickness.

② AP ArmaFlex meets MIL-P-15280J, FORM S and MIL-C-3133C (MIL STD 670B) Grade SBE through 1" thickness.

③ AP ArmaFlex and AP ArmaFlex FS Sheet and Roll Insulation withstand temperature of 250°F [121°C] when tested according to ASTM C 411. "Test Method for Surface Performance of High-Temperature Insulations." At this temperature, AP ArmaFlex Sheet and Roll Insulation shows no evidence of flaming, glowing, smoldering, delamination, melting or insulation collapse. Although this insulation will withstand high temperatures, continuous use temperature should be limited to 220°F [105°C].

④ AP ArmaFlex FS is formulated with EPDM rubber giving it a higher upper use temperature than AP ArmaFlex.

⑤ At temperatures below -20°F [-29°C], elastomeric insulation starts to become less flexible. However, this characteristic does not affect thermal efficiency and resistance to water vapor permeability of ArmaFlex insulation.

⑥ For applications of -40°F to -297°F [-40°C to -183°C], contact Armacell.



TECHNICAL DATA – AP ArmaFlex® and AP ArmaFlex® FS SHEET AND ROLL INSULATION

R-Value	R-1.0	R-1.5	R-2.1	R-3.1	R-4.2	R-6	R-8
Thickness:	1/4" (6 mm)	3/8" (10 mm)	1/2" (13 mm)	3/4" (19 mm)	1" (25 mm)	1-1/2" (38 mm)	2" (50 mm)
Sound Absorption Coefficients Frequency	125Hz	125Hz	125Hz	125Hz	125Hz	125Hz	125Hz
Thickness Nom. 1" (25 mm)	0.01	0.13	0.39	0.69	0.29	0.26	0.38
Thickness Nom. 1-1/2" (38 mm)	0.07	0.26	0.92	0.31	0.49	0.53	0.49
Thickness Nom. 2" (50 mm)	0.14	0.62	0.44	0.43	0.51	0.45	0.51
Sizes							
Sheet: Width x Length	36" x 48" (.915 m x 1.22 m)						
Thickness (nominal)	1/8", 1/4", 3/8", 1/2", 3/4", 1", 1-1/2" & 2" (3, 6, 10, 13, 19, 25, 38 & 50 mm)						
Roll: Width	48" (1.22 m)						
Thickness (nominal) x Length	1/4" x 140' (6 mm x 42.6 m)			1" x 35' (25 mm x 10.7 m)			
	3/8" x 100' (10 mm x 30.5 m)			1-1/2" x 25' (38 mm x 7.6 m)			
	1/2" x 70' (13 mm x 21.4 m)			2" x 18' (50 mm x 5.4 m)			
	3/4" x 50' (19 mm x 15.2 m)						
Outdoor Use	Painting with WB Finish or other protective jacketing is required to prevent damage to the insulation in exterior applications and to comply with the insulation protection sections of the International Energy Conservation Code (IECC) and ASHRAE 90.1.						



GREENGUARD Certified products are certified to GREENGUARD standards for low chemical emissions into indoor air during product usage. For more information, visit ul.com/gg.

Microban antimicrobial product protection is limited to the product itself and is not designed to protect the users of these products from disease causing microorganisms, or as a substitute for normal cleaning and hygiene practices. Microban International, Ltd. makes neither direct nor implied health claims for the products containing Microban® antimicrobial product protection. Data, photomicrographs and information presented are based on standard laboratory tests and are provided for comparative purposes to substantiate antimicrobial activity for non-public health uses. Microban is a registered trademark of Microban International, Ltd.

All data and technical information are based on results achieved under typical application conditions. It is the customer's responsibility to verify if the product is suitable for the intended application. The responsibility for professional and correct installation and compliance with relevant building regulations lies with the customer. By ordering/receiving product you accept the **Armacell General Terms and Conditions of Sale** applicable in the region. Please request a copy if you have not received these.

© Armacell, 2018. AP ArmaFlex is a trademark of the Armacell Group

AP ArmaFlex and AP ArmaFlex FS | Sheet and Roll Insulation TDS | 082018 | NA | EN-A | 015

ABOUT ARMACELL

As the inventors of flexible foam for equipment insulation and a leading provider of engineered foams, Armacell develops innovative and safe thermal, acoustic and mechanical solutions that create sustainable value for its customers. Armacell's products significantly contribute to global energy efficiency making a difference around the world every day. With 3,000 employees and 26 production plants in 17 countries, the company operates two main businesses, Advanced Insulation and Engineered Foams. Armacell focuses on insulation materials for technical equipment, high-performance foams for high-tech and lightweight applications and next generation aerogel blanket technology.

For more information, please visit:
www.armacell.us
800-866-5638

