

# Polyco VP Adhesive

specification data

**Use:** Bonding Polyco PVC Jacket.

**Color:** White and Clear.

**Base:** PVC Resin.

**Volatile Material:** Tetrahydrofuran, cyclohexanone.

**% Solids:** 15%.

**Viscosity:** 1200 CPS.

**Bonding Time:** 20% strength immediately.  
80% within 2 hours.  
100% within 24 hours.

**Shelf Life:** 1 year.

**Solvents for Clean Up:** MEK (Methylethylkeytone).

**Service Temperature:** -25° to 140°F.

**Flash Point:** -7° F.

**Waybill Notation:** Cement N.O.S. (Red Label Required).

Conforms to ASTM D-2564. NSF and USDA Approved

## Precautions

**Extremely Flammable.** Do not use in confined areas as high concentration of vapors may be harmful.



### Speedline Corporation

6810 Cochran Road · Solon, OH 44139

Toll Free: **1.800.551.9759** · Tel: 1.800.551.9759 · Fax: 1.440.914.9334

#### OHIO

6810 Cochran Road  
Solon, OH 44139  
Tel: 1.800.551.9759

#### NORTH CAROLINA

501 West Camel Street  
Greenboro, NC 27401  
Tel: 1.800.551.9760

#### CALIFORNIA

4283 Pock Lane #200  
Stockton, CA 95206  
Tel: 1.800.833.4500

#### TEXAS

8905 Market Street  
Houston, TX 77029  
1.800.874.1748